

Polyester needlepunched nonwoven geotextile, smooth colour, no chemical binders.

TECHNICAL DATASHEET

		200	U.o.M.
Functions		S + F + D	
Applications		UNI EN 13249 UNI EN 13250 UNI EN 13251 UNI EN 13252 UNI EN 13253 UNI EN 13254 UNI EN 13255 UNI EN 13256 UNI EN 13257 UNI EN 13265	
Weight	EN ISO 9864	200 ±10	g/m ²
	Tolerance %		
Composition		100% Polyester	
Certifications		CE 1213-CPD-4884	
Tensile strength	MD	2,2	kN/m
	Tolerance	-0,5	
	CD	2,3	
	Tolerance	-0,5	
CBR puncture test	EN ISO 12236	0,4 -0,10	kN
	Tolerance		
Dynamic perforation (cone drop test)	EN ISO 13433	40 +5,00	mm
	Tolerance		
Water flow capacity	EN ISO 12958	4,90x10 ⁻³ ±1,47x10 ⁻³	l/sm
	Tolerance		
Water flow rate	EN ISO 11058	94 -20	l/m ² s
	Tolerance		
Characteristic opening size	EN ISO 12956	86 ±20	µm
	Tolerance		
Weathering resistance	EN 12224	To be covered within 14 days after the installation	
Hydrolysis resistance	EN 12447	Durability expectation 5 years for normal soil with 4 < pH < 9 and temperature < 25 °C	