

CHARACTERISTICS

- Black cross-linked, closed-cell, polyethylene foam coated on both sides with an acrylic adhesive
- Offers very high peel and shear properties
- Is produced in a self wound form on a paper liner
- Resistant to water, detergents, alcohols, aliphatic and some aromatic solvents



APPLICATIONS

- Bonding of divided lites

TECHNICAL CHARACTERISTICS	
Croisifix 0,8 mm	
Peel 180° - 30 min on stainless steel : FTM1	>25 N/25 mm
Peel : AFERA 4001	23°C: > 25 N/25 mm 70°C: > 5 N/25 mm
Shear on stainless steel 1 kg – 25 mm x 25 mm : FTM 8	> 1000 hours
Shear : AFERA 4012	23°C: > 90 N 70°C: > 25 N
Tensile : DIN 53455	MD 14 N/15 mm CD 10 N/15 mm
Elongation : DIN 53455	MD 350 % CD 350 %
Density	100 kg/m ³
Minimum application temperature	+10°C
Temperature resistance	-40°C - +100°C
Shelf life, in the original packing in dry conditions between +15°C - +25°C at 50% R.H.	2 years

PACKING AND MEASUREMENTS	
Measurement	Packing
0,8 x 12 mm	26 rolls of 66 m/box
0,8 x 19 mm	16 rolls of 66 m/box
0,8 x 25 mm	12 rolls of 66 m/box
0,8 x 30 mm	10 rolls of 66 m/box

METHOD OF USE

Preparation

The surface must be rigid (remove the parts that can detach), dry, free of grease and dust.

Rough spots and unevenness must be minimum

If surface is degreased with alcohol, make sure that it is dry before you use the adhesive strip.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.