



CHARACTERISTICS

- Solvent-based plasto-elastic bituminous sealant
- Reinforced by fibers
- After curing a permanent plasto-elastic mass is formed
- Has a high resistance to fire or distortion
- Can be used (cold) immediately after unwrapping and economic in use
- Is tixothrope and therefore cannot drip, flow or spill and makes no threads
- Free from asbestos
- Resistant to moisture, protects against rust and moisture.
- Highly insulating

APPLICATIONS

- For gluing and reparations on bituminous surfaces
- Waterproof sealing of joints, seams, rooftop fences, skylights, chimneys, ventilation tubes, drainpipes, etc.
- Adhesive for insulating panels (does not corrode the insulating material)
- To fill leaks and performing (emergency) reparations on rooftops
- Reparation of tectyling layer under cars, caravans, etc.
- Sealing seams in wooden ships or boats
- Immediate and permanent adhesion on all common construction materials, such as brick, concrete, lead, zinc, tiles, isolation panels, certain plastics, etc.

TECHNICAL CHARACTERISTICS	
Basis	Bitum
Curing system	Neutral, physical dryness
Character	Plasto-elastic
Flash point	63°C
Viscosity 100°C	5 poise
Viscosity 75°C	7,2 poise
Solid matter	ca 88%
Density: ISO 1183	1,29 g/ml
Application temperature	+8°C - +30°C
Shelf life, if kept in the original packing and stored in cool and dry conditions.	12 months

PACKING AND COLOURS
25 cartridges of 310 ml/box - 48 boxes/pallet
Black
Can 6 kg - 96 cans/pallet: not in stock - only available upon request per pallet
Black

METHOD OF USE

Preparation

All surfaces should be dry, free from dust or grease.

Primers

On very porous surfaces **Paraphalt Primer** should be applied.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.

Application

- To be applied with a spatula or by means of a cartridge.
- Cartridge: it is important that the nozzle is clean and the opening sufficiently large.
- For a perfect adhesion, a maximum space of 3 mm is allowed between the surface and the top of the nozzle.
- Should be applied in strips or spots, for a good evaporation of the solvent

Cleaning

Mechanically with filling-knife, turpentine or xylene.

LIMITATIONS

- Can only be used for synthetic materials without softener
- Compatibility with extruded polystyrene varies. In this case the **Paraphalt Bitumen** must be put on the surface and never on the polystyrene
- Contact with mineral oils softens the product

SAFETY

Safety data sheet available on request.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.